


 0965
POLYTECHNISCH BEDRIJF BVBA/SPRL – P.T.B.-COMPAKTUNA® INDUSTRIEPARK ZWIJNAARDE 6 9052 GENT – BELGIUM
13 009/CPR/130701 EN 934-2+A1 P.T.B.-ANTIGEL Bindingsversneller/Accélérateur de prise/Bonding accelerator/Bindung Beschleuniger EN 934-2+A1,T.6
Chloride gehalte/Teneur en chlorure/Chloride content/ Chlorid Gehalt < 28,5% m/m Alkali gehalte/Teneur en alcalins/Alkali content/ Alkali Gehalt < 2,0% m/m Corrosief gedrag / Comportement à la corrosion /Corrosion behaviour/ Korrosionsverhalten: contains chloride. See chloride content.




Characteristics

- Bonding accelerator
- Plasticizing action
- Improves the strength
- Smooth from stripping



Dosage

- Add 2 L P.T.B.-ANTIGEL for 50 kg cement to the make-up water.
- Use P.T.B.-ANTIGEL only with Portland or blast furnace cement
- Use P.T.B.-ANTIGEL only at max. -5°C !



Remarks

- Cannot be used in armed concrete
- Contains chloride

Mixing ratio	Consumption	Packaging
Add undiluted to the make-up water	max. 2 l for 50 kg of cement	2 l (20 pcs/cardboard box), 5 l and 10 l
Colours		Application temperature
Colourless	Avoid contact with the skin	from 0°C till + 30 °C

As the applications of our products are diverse, no single application guideline can be laid down. All product data reflect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignificant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our "technical department" which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding.