



P.T.B.-PRIMER

Solvent free



Applications

Ready-to-use, colourless primer for walls, floors, and ceilings. P.T.B.-PRIMER lowers porosity and reinforces the substrate. Suitable surfaces are: plaster work on cement base, plaster work on gypsum base, gypsum plaster board, gypsum plaster blocks, concrete, ... P.T.B.-PRIMER is suitable for indoor as well as outdoor use.



Directions for use

P.T.B.-PRIMER should always be applied to a porous, clean, healthy, dust and oilfree substrate. Shake well before use.

P.T.B.-PRIMER should be generously and undilutedly applied with a brush or a roller. Strongly absorbing undergrounds (such as aerated concrete, plasterwork on gypsum base, and the like) should be treated twice.

Drying time: about 2 to 3 hours.




Special applications

P.T.B.-PRIMER can be used as basic layer - on the adhesive side - to protect certain types of natural stone (for instance, white marble) against spot blemishes and staining. To be applied in 1 or 2 layers. It is recommended that a test be carried out first.

Remarks

- The application tools should be cleaned with water directly after use.
- Do not use at temperatures below + 5°C or on top of a substrate where the temperature is below + 5°C.
- Store in a dry and frost-free place.

The VOC content of P.T.B.-PRIMER is lower than 3%.



Mixing ratio	Consumption	Packaging
Undiluted	± 0,050 to 0,150 l/m ² , depending on the porosity of the substrate	1l and 5 l
Colours	Temps de séchage	Application temperature
Becomes colourless after application	± 2 to 3 hours	+ 5°C till + 30°C

As the applications of our products are diverse, no single application guideline can be laid down. All product data reflect the state of knowledge of our products at the time of publication. Therefore all suggestions and recommendations concerning the use of our products are merely illustrative. Apply the product on a small and insignificant spot before starting to use our products to be sure the desired result is obtained. Always ask for the technical sheet of our products. Visit the website www.compaktuna.be. Consult our "technical department" which can be reached for free on the green number 0800/92279. The Dutch text shall be exclusively binding. Version 10/02/2014.

BV POLYTECHNISCH BEDRIJF is EN ISO 9001 certified



P.T.B.-COMPAKTUNA®
Industriepark - Zwijnaarde 6
9052 Gent - België
Tel.: +32 9 221 11 16
Fax.: +32 9 221 85 01
RPR Gent RPM
E-mail: info@compaktuna.be
Website: www.compaktuna.be
Oms groen nummer: 0800/92279