

MIX M15

Ready-to-use masonry mortar

CE 07	
COMPAKTUNA® bv/srl INDUSTRIEPARK ZWIJNAARDE 6 9052 GENT – BELGIUM 0965	
017/CPR/180323 EN 998-2:2016 MIX M15 Dry masonry mortar for normal use/performance mortar/internal and external use TYPE G	
Compressive strength Water absorption Contents of chloride	Class: M15 kg/m²min ^{0.5} : 0,4 max. 0,02%



CHARACTERISTICS



+30 °C

+5 °C

Ready-to-use dry masonry mortar composed of cleaned and sieved sand, cement, aggregates of exceptional quality.

In addition to a very plastic workability and high resistance, MIX M15 has the advantage that after mixing with water, the mortar remains homogeneous (no water comes on the mortar).

Given its high compressive strength, MIX M15 is suitable for load-bearing masonry.

Technical characteristics		Meets requirement according to NBN EN 998-2
Compressive strength (after 28 days)		≥ 15 N/mm² => M15
Water absorption		0,4 kg/m² .min ^{0.5}
Mixing ratio	Consumption	Packaging
±4 L water per 25 kg bag (±16%)	Depending on stone width and joint thickness	10 & 25 kg PE
Colour	Processing time	Application temperature
Grey	±3 hours	+5 °C to +30 °C

MIX M15

DIRECTIONS FOR USE

MIX M15 is mixed with approximately 16% water, i.e. approximately 4 L of water to 25 kg of product. Protect drying masonry from frost, precipitation, strong winds and direct sunlight. The works must be protected from cold, driving rain and wind.

PACKAGING

MIX M15 is available in grey colour in polyethylene bags of 25 kg and 10 kg. The shelf life is 12 months in the original, closed packaging and stored dry.

