



Product data
Floorify® Rigid Vinyl Planks & Tiles
 click



version: 1/02/2021

EN












Dimensions and basic data







		Large Planks	Planks XL	Herringbone	Tiles	
Width	ISO24337	225	240	125	600	mm
Length	ISO24337	1524	2000	750	900	mm
Number of panels per pack	-	8	5	24	4	pc
m ² per pack	-	2,74	2,4	2,25	2,16	m ²
Weight per pack	ISO23997	22	20	20,08	17,6	kg
Total thickness	ISO24337	4,5	4,5	4,5	4,5	mm
Top Layer thickness	EN429	0,55	0,55	0,55	0,55	mm
Core	-	Sound reducing, robust and waterproof Floorify® Rigid Core				
Finish	-	Protected with stain resistant Floorify® Quiet Sense Technology				
Locking method	-	Traditional glueless click under license of Unilin.				

Warranty

	Usage class	ISO10582	33
	CE	EN 14041	DoP FF001
	Warranty	Residential use	25 years

Technical data

	Norm	Norm Requirements	Floorify® results
	EN13329, Annex E	≥ 2000 cycles	≥ 4000 cycles - AC4
	EN13329	≥ 1600 mm	In combination with Floorify® Comfort underlay: > 1800mm - IC3
	ISO24343-1	≤ 0,2 mm	In combination with Floorify® Comfort underlay: no visible changes
	EN423	Groups 1 and 2: grade 5; Group 3: grade 4	Groups 1, 2 and 3: grade 5
	ISO 105-B02:1994, Method 3a	≥ 6	> 6
	EN 13501-1 ISO 9239-1	-	Bfl-s1
	EN ISO23999 6uur bij 80C	≤ 0,25 %	≤ 0,10 %
	ISO24334	Long side: ≥ 1kN/m Short side: ≥ 1,5kN/m	Long side: > 8kN/m Short side: > 8kN/m (n/a herringbone)
	EN424	No visible changes	No changes
	EN425	≥ 25000 cycles: No delamination, no disturbance	In combination with Floorify® Comfort underlay: no visible changes
	EN13893 DIN 51130:2014	- -	DS R10

	Swelling	ISO24336	≤ 18%	0%
	Thermal resistance (floor + underlay)	EN12667	< 0,15R (m²K/W)	0,0686R (m²K/W) (0,0146 floor + 0,0540 underlay)
	Floor heating	Appropriate for all standard heating systems IN cement flooring. NOT appropriate for heating films.		
	Impact sound improvement	ISO712	ΔLw18Db	In combination with Floorify® Comfort underlay: ΔLw21Db (ΔLlin10Db)
Dangerous Substances				
	Formaldehyde emission	EN14041	-	E1
	TVOC 28 days	< 1000µg/m³	-	< 10µg/m³
	Emissions in the interior air	Decree n° 2011-321	-	A+
	REACH	-	-	Floorify® floors and accessories are fully REACH compliant
	Plasticizers	-	-	DOPT - virgin PVC - 100% orthophtalate free

Floorify NV reserves the right to make alterations to material and structures when this serves to improve the quality
Floorify NV, Noordstraat 140, B-8800 ROESELARE, BELGIUM - Email: sales@Floorify.com - T/ +32 (0)51 140 180