



Technical data sheet

PROTECTION MADE EASY

ADDITIVE MCU HB

Description and destination of the product

By adding **Additive MCU HB** to moisture curing PU paints (MCU), the maximum allowed layer thickness can be obtained during application without any risk of blisters.

Additive MCU HB can be added to ***Polysilco HS***, ***Polymicace*** and ***Polyguard***.

Colour

Colourless.

Technical data

Density: 0.87 (\pm 0.03) kg/L

Surface preparation

Add 0.2 L of **Additive MCU HB** to 5 L ***Polysilco HS***, ***Polymicace*** or ***Polyguard***.

This additive **cannot** be used in ***Polyfix*** and ***Polygloss***.

For a 10 L packing of MCU, 2 packings of **Additive MCU HB** are thus added.

If this additive is used for a 1L packing, the following must be weighed:

35 g **Additive MCU HB** for 1 L MCU-product

After opening this additive, it must be very well closed after use.

After adding the additive, the paint has a potlife of about 7 hours.

Once the additive is added, the paint **cannot** longer be kept than 7 hours. After 7 hours the paint can also not be used any longer.

Storage stability

Minimum 1 year, stored in a dry environment (frost-free) at temperatures between +5°C and +40°C, in the original unopened packing.

Safety measure

For detailed information about safety measures, personal protection and transport data of this product, we refer to the safety data sheet.

The last update of our technical data sheets is always available at our website: www.libertpaints.com

Disclaimer

The information given in this technical data sheet is only a general product description, based on our experiences and tests and therefore does not represent a specific practical case. Consequently Libert Paints doesn't guarantee the functionality or result and takes no responsibility in this respect.

We advise our clients to test the applicability of the product to the nature and the state of the surfaces and to carry out the necessary representative tests in case of doubt. Please contact our R&D department as the occasion arises.

Attention: our clients should verify whether the present technical data sheet hasn't been replaced by a more recent version.